





Shieldex[®] Köln

1300431100

Shielding effectiveness 0.2 - 14 GHz according to IEEE 299/2006





Shieldex[®] Köln

1300431100



Raw Material	100 % Polyamide / Nylon 6.6
Non-woven	Cerex [®] 1.5 oz spunbonded
Metal Plated	Copper
Material Composition	(45 % PA / 50.5 % Cu / 4.5 % CR Coating) ± 20 %
+ CR Coating	Protective acrylic coating
Electrical Surface Resistivity	< 0.02 Ω/□
Measured Frequency	0.2 GHz – 14 GHz
Shielding Effectiveness	Up to 77 dB
Abrasion Resistance	≥ 20000 cycles
Total Weight	80 g/m ² ± 20 %
Total Thickness	0.160 mm ± 20 %
Roll Width	100 ± 3 cm
Roll Length	Average 200 m
Temperature Range	-30 °C to 90 °C
Storage and Handling	According to our care and handling instructions
Compliance and Certification	DIN EN ISO 9001:2015, REACH, RoHS

Alterations Reserved 05.09.2024/10 – The above information has been compiled from our manufacturer area according to the latest state of development and application technology. Since application and further processing are beyond our control, no liability of the producer can be derived from the contents of the data sheet. All deviant or transcending data sheet information must be confirmed in written form by the manufacturer. Our general terms and conditions apply in all cases. All previous data sheets are invalid with the publication of this data sheet. Please note our handling and storage instructions as well accessible at www.shieldex.de.