
shielde<u>x</u>



Shieldex® Porto PES PW

1502101136 Preliminary



shielde<u>x</u>



Shieldex® Porto PES PW

1502101136 Preliminary

Raw Material 100 % Polyester

Weave Plainweave

Thread density warp $\approx 580 \, \text{threads/dm}$ Thread density weft $\approx 450 \, \text{threads/dm}$

Metal Plated Copper + Tin

Material Composition $(31 \% PES / 65 \% Cu / 4 \% Sn) \pm 10 \%$

Electrical Surface Resistivity $\leq 0.02 \Omega /\Box$

Measured Frequency 0.2 GHz – 14 GHz

Shielding Effectiveness 1Average of < 91 dB from 0.2 GHz - 2 GHzShielding Effectiveness 2Average of < 86 dB from 2 GHz - 5 GHzShielding Effectiveness 3Average of < 87 dB from 5 GHz - 14 GHz

Total Weight $100 \text{ g/m}^2 \pm 20 \%$ Total Thickness $0.08 \text{ mm} \pm 20\%$

Roll Width 135 cm /- 3 cm/+2 cm

Roll Length < 200 m

Temperature Range $-30 \,^{\circ}\text{C}$ to $90 \,^{\circ}\text{C}$

Storage and Handling According to our care and handling instructions

Compliance and Certification DIN EN ISO 9001:2015, REACH, RoHS

Alterations Reserved 10.10.23/02 — The above information has been compiled from our manufacturer area according to the latest state of development and application technology. Since application and further processing are beyond our control, no liability of the producer can be derived from the contents of the data sheet. All deviant or transcending data sheet information must be confirmed in written form by the manufacturer. Our general terms and conditions apply in all cases. All previous data sheets are invalid with the publication of this data sheet. Please note our handling and storage instructions as well accessible at www.shieldex.de.

