

Ag	Cu	Ni	Sn
----	----	----	----

Shieldex® Bremen FR

110010180FR



Raw Material	100 % Polyamide / Nylon 6.6
Weave	Ripstop
Thread density warp	≈ 480-500 threads/dm
Thread density weft	≈ 450-490 threads/dm
Metal Plated	Silver
Coating	FR Coating
Electrical Surface Resistivity /Metallic side	Average < 0.3 Ω/□
Electrical Surface Resistivity /FR Coated side	Average < 0.3 Ω/□
Total Weight	240 g/m ² ± 15 %
Total Thickness	0.24 mm ± 20 %
Roll Width	134 ± 3 cm
Storage and Handling	According to our care and handling instructions
Compliance and Certification	DIN EN ISO 9001:2015
Fire Resistance Rating	Euro class E /Tested according to EN 13501-1:2019 CS / FAR 25.853 (a) Appendix F Part I

Alterations Reserved 02.09.2026/02 – The above information has been compiled from our manufacturer area according to the latest state of development and application technology. Since application and further processing are beyond our control, no liability of the producer can be derived from the contents of the data sheet. All deviant or transcending data sheet information must be confirmed in written form by the manufacturer. Our general terms and conditions apply in all cases. All previous data sheets are invalid with the publication of this data sheet. Please note our handling and storage instructions as well accessible at www.shieldex.de.